

CARGILLE LABORATORIES

55 Commerce Road • Cedar Grove • New Jersey • 07009 – 1289 USA
 Ph: 973-239-6633 • Fax: 973-239-6096 • CargilleLabs@cargille.com • www.Cargille.com

Immersion Oil Type B

18-July-2018

n (589.3nm) 23°C = 1.5150

TYPICAL CHARACTERISTICS

<u>COMPOSITION</u>	Aliphatic and Alicyclic Hydrocarbons, Polybutenes and Hydrogenated Terphenyls
<u>APPEARANCE</u>	Colorless Liquid to slightly yellow
<u>COLOR STABILITY IN DIRECT SUN</u>	In direct sunlight will slightly darken in days, more after 4 months
<u>INDEX CHANGE RATE BY EVAPORATION</u>	Very Low: 0.00000 expected: Exposed surface area to volume ratio of 0.2 cm ² /cc @ 25°C for 32 days
<u>ODOR</u>	Slight, characteristic
<u>FREEZING POINT</u> °C	< -13
<u>BOILING POINT</u> °C @ 760mm Hg	Approx. 340
<u>FLASH POINT</u> °C C.O.C.	Approx. 163
<u>DENSITY</u> g/cc @ 23°C	0.923
<u>COEF. OF THERM. EXP.</u> cc/cc/°C	0.0006
<u>VISCOSITY</u> @ 23°C	1250cSt -- 1153cP

SOLUBLE: Carbon Tetrachloride, Diethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene
INSOLUBLE: Ethanol, Water (To Clean off Glass: Use wipe and Acetone)

COMPATIBLE: 10-month immersion at 25°C: Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Latex Rubber, Neoprene, Fluorosilicone (Silastic 730 RTV), Silicone (Sylgard 184, 3140 RTV) Rubbers, Tygon F-4040-A, Tygothane, Aluminum, Copper, Brass, Steel; (tests done on one example of each).

INCOMPATIBLE: Polystyrene, Tygon S-50-HL, R-3603, B-44-3

CAUCHY EQUATION: Refractive index as a function of wavelength at 23.0°C

W = wavelength (nm)

$$n(W) = 1.498304 + (5.456721E+03) / W^2 + (1.203987E+08) / W^4$$

SOURCE OR SPECTRAL LINE	WAVELENGTH (nm)	REFRACTIVE INDEX 23°C	% TRANSMITTANCE 25°C		
			1 mm	1 cm	10 cm
near UV cut off	350.0	1.551	77	7	0
i (Hg)	365.0	1.546	93	50	0
h (Hg)	404.7	1.5361	98	85	19
F' (Cd)	480.0	1.5243	100	96	69
F (H)	486.1	1.5236	100	97	74
e (Hg)	546.1	1.5180	100	99	91
D (Na D1, D2 mean)	589.3	1.5150	100	100	98
HeNe laser	632.8	1.5127	100	100	99
C' (Cd)	643.9	1.5122	100	100	99
C (H)	656.3	1.5116	100	100	99
Ruby Laser	694.3	1.5101	100	100	98
GaAs laser	840	1.5063	100	100	96
Nd: YAG laser	1064	1.503	100	97	76
Diode	1300	1.502	99	91	37
Diode	1550	1.501	98	83	16
n _F - n _C	=	0.0120			
Abbe v _D : (n _D - 1)/(n _F - n _C)	=	42.9			
Abbe v _e : (n _e - 1)/(n _F - n _C)	=	42.8			
Temp. coef: dn _D /dt 15 - 35°C	=	-0.00031			

The above values are typical for this liquid and are calculated from values typical of its components