



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1806

Typical Characteristics

Refractive Index Liquid **Series AA**
Refractive Index **1.41400** at 589.3 nm and 25 ° C

Composition Siloxane and Aliphatic / Alicyclic Hydrocarbons
Appearance Colorless Liquid
Odor None
Color Stability In Direct Sun: no visible change after 10 years
Index Change Rate Very Low : 0.00000 to +0.00001
by Evaporation expected after 32 days with exposed surface area to volume ratio of 0.2 cm²/cc @ 25 °C

Index at 20°C 1.41603
Pour Point < -7 °C
Boiling Point > 200 °C (760 mm Hg)
Flash Point > 138 °C (COC)
Brix Value (Per ICUMSA) **48.1 at 20°C**
Density 0.906 g / cc at 25 °C
Density Temp Coef -0.0009 g / cc / °C
Coef of Thermal Expansion 0.0010 cc / cc / °C
Thermal Conductivity 0.0003 cal / sec / cm² / °C - 1 cm thickness

Viscosity 11 cSt at 25 °C 10 cP at 25 °C
Surface Tension 20 dynes/cm at 25 °C

Soluble Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene

Partly Soluble Acetone

Insoluble Ethanol, Water

Compatible 1 Month Immersion at 25 °C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polystyrene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Neoprene and Fluorosilicone (Silastic 730 RTV) Rubbers ; Tygon F-4040-A, Tygothane, Aluminum, Brass, Copper, Steel

Incompatible Latex, Silicone (Sylgard 184 and 3140 RTV) Rubber, Tygon S-50-HL, R-3603, B-44-3



Refractive Index Liquid **Series AA**
 Refractive Index **1.41400** at 589.3 nm and 25 °C

Cauchy Coefficients
 A 1.401950E+00 B 4.2564E+03 C -2.4961267E+07

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	1.48	97	71	3	0
240.0	1.47	99	90	37	0
250.0	1.46	99	92	44	0
270.0	1.46	99	94	52	0
290.0	1.45	100	98	79	10
308.0	1.44	100	99	89	32
355.0	1.434	100	100	99	88
365.0	1.432	100	100	100	96
406.0	1.4269	100	100	100	96
473.0	1.4205	100	100	100	97
532.0	1.4167	100	100	100	98
589.3	1.4140	100	100	100	98
632.8	1.4124	100	100	100	98
656.3	1.4117	100	100	100	98
790.0	1.4087	100	100	100	99
828.0	1.4081	100	100	99	92
981.0	1.406	100	100	97	76
1310.0	1.404	100	99	94	53
1550.0	1.404	100	96	67	2
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

($n_F - n_C$) 0.0078

Abbe v_D 52.9

Temp. Coefficient -0.000406 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening