



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1806

Typical Characteristics

Refractive Index Liquid **Series AA**
Refractive Index **1.43200** at 589.3 nm and 25 ° C

Composition Siloxane and Aliphatic / Alicyclic Hydrocarbons
Appearance Colorless Liquid
Odor None
Color Stability In Direct Sun: no visible change after 10 years
Index Change Rate Very Low : 0.00000 to +0.00001
by Evaporation expected after 32 days with exposed surface area to volume ratio of 0.2 cm²/cc @ 25 °C

Index at 20°C 1.43399
Pour Point < -7 °C
Boiling Point > 200 °C (760 mm Hg)
Flash Point > 138 °C (COC)
Brix Value (Per ICUMSA) **56.5 at 20°C**
Density 0.874 g / cc at 25 °C
Density Temp Coef -0.0008 g / cc / °C
Coef of Thermal Expansion 0.0009 cc / cc / °C
Thermal Conductivity 0.0003 cal / sec / cm² / °C - 1 cm thickness

Viscosity 14 cSt at 25 °C 12 cP at 25 °C
Surface Tension 21 dynes/cm at 25 °C

Soluble Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene

Partly Soluble Acetone

Insoluble Ethanol, Water

Compatible 1 Month Immersion at 25 °C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polystyrene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Neoprene and Fluorosilicone (Silastic 730 RTV) Rubbers ; Tygon F-4040-A, Tygothane, Aluminum, Brass, Copper, Steel

Incompatible Latex, Silicone (Sylgard 184 and 3140 RTV) Rubber, Tygon S-50-HL, R-3603, B-44-3



Refractive Index Liquid **Series AA**
 Refractive Index **1.43200** at 589.3 nm and 25 °C

Cauchy Coefficients
 A 1.420055E+00 B 4.1477E+03 C 1.6249954E+05

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	1.50	95	62	1	0
240.0	1.49	99	89	33	0
250.0	1.49	99	93	47	0
270.0	1.48	99	92	43	0
290.0	1.47	100	98	81	12
308.0	1.46	100	99	87	24
355.0	1.453	100	100	98	85
365.0	1.451	100	100	99	91
406.0	1.4452	100	100	99	91
473.0	1.4386	100	100	100	96
532.0	1.4347	100	100	100	97
589.3	1.4320	100	100	100	97
632.8	1.4304	100	100	100	97
656.3	1.4297	100	100	100	97
790.0	1.4267	100	100	100	99
828.0	1.4261	100	100	99	94
981.0	1.424	100	100	96	67
1310.0	1.422	100	99	91	41
1550.0	1.422	100	97	73	4
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

($n_F - n_C$) 0.0079

Abbe v_D 54.5

Temp. Coefficient -0.000398 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening