



**Cargille Laboratories**  
**55 Commerce Rd - Cedar Grove, NJ 07009-1289**  
**Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com**

Catalog # 1806

Typical Characteristics

Refractive Index Liquid                    **Series AA**  
Refractive Index                            **1.43600**      at    589.3 nm    and            25            ° C

---

Composition                                Siloxane and Aliphatic / Alicyclic Hydrocarbons  
Appearance                                Colorless Liquid  
Odor    None  
Color Stability                              In Direct Sun: no visible change after 10 years  
Index Change Rate                        Very Low : 0.00000 to +0.00001  
by Evaporation                            expected after 32 days with exposed surface area to volume ratio of 0.2 cm<sup>2</sup>/cc @ 25 °C

---

Index at 20°C                                1.43798  
Pour Point                                    < -7 °C  
Boiling Point                                > 200 °C ( 760 mm Hg )  
Flash Point                                  > 138 °C ( COC )  
**Brix Value (Per ICUMSA)**                **58.2 at 20°C**  
Density                                        0.867 g / cc at 25 °C  
Density Temp Coef                        -0.0008 g / cc / °C  
Coef of Thermal Expansion              0.0009 cc / cc / °C  
Thermal Conductivity                      0.0003 cal / sec / cm<sup>2</sup> / °C - 1 cm thickness  
  
Viscosity                                      14 cSt at 25 °C                                12 cP at 25 °C  
Surface Tension                              21 dynes/cm at 25 °C

---

Soluble                                        Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene  
  
Partly Soluble                                Acetone  
  
Insoluble                                        Ethanol, Water

---

Compatible                                    1 Month Immersion at 25 °C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polystyrene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Neoprene and Fluorosilicone ( Silastic 730 RTV ) Rubbers ; Tygon F-4040-A, Tygothane, Aluminum, Brass, Copper, Steel  
  
Incompatible                                  Latex, Silicone ( Sylgard 184 and 3140 RTV ) Rubber, Tygon S-50-HL, R-3603, B-44-3

---



Refractive Index Liquid **Series AA**  
 Refractive Index **1.43600** at 589.3 nm and 25 °C

Cauchy Coefficients  
 A 1.424078E+00 B 4.1235E+03 C 5.7455587E+06

Cauchy Equation at 25°C  $A + B / \lambda^2 + C / \lambda^4$  ( $\lambda$  = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	1.51	95	61	1	0
240.0	1.50	99	89	32	0
250.0	1.49	99	93	47	0
270.0	1.48	99	91	41	0
290.0	1.47	100	98	82	13
308.0	1.47	100	99	86	23
355.0	1.457	100	100	98	85
365.0	1.455	100	100	99	91
406.0	1.4493	100	100	99	91
473.0	1.4426	100	100	100	95
532.0	1.4387	100	100	100	97
589.3	1.4360	100	100	100	97
632.8	1.4344	100	100	100	97
656.3	1.4337	100	100	100	97
790.0	1.4307	100	100	100	99
828.0	1.4301	100	100	99	94
981.0	1.428	100	100	96	65
1310.0	1.426	100	99	91	38
1550.0	1.426	100	97	74	5
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

( $n_F - n_C$ ) 0.0079

Abbe  $v_D$  54.8

Temp. Coefficient -0.000397  $dn_D/dt$  (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening